

thoenes[®] SL TRD 401


thoenes[®] SL TRD 401 is a gasket material based on graphite with stainless steel foil insert. The stainless steel foil insert achieves a higher surface load. The material has excellent resistance to chemicals and heat. Due to the very high creep resistance and the very high compressibility, the sealing material can be used under demanding conditions in the chemical and petrochemical industry.

- Basis:** Expanded natural graphite (purity > 99 %), stainless steel foil insert
- Colour:** Black
- Surface coating:** Standard - without non-stick coating
- Certifications:** DIN-DVGW, KTW, HTB
- Applications:** Use in gas supply, compressors and pumps. Ideal sealing material under high temperatures and pressures, during mechanical and thermal cycles and shock loads. Expanded graphite is suitable for steam and for almost all chemical media, except for strongly oxidizing, such as nitric and chromic acid.

Technical specifications (typical values 2 mm thickness)

Description	DIN 28091-4		GR-10-0-1K-Cr
Density	DIN 28090-2	g/cm ³	1.3
Compressibility	ASTM F 36/A	%	42
Resilience	ASTM F 36/A	%	15
Pressure resistance	DIN 52913		
50 MPa, T= 300°C, 16 h		MPa	49
Specific leakage rate	DIN 3535/6	mg/m*s	0.05
Leachable chloride content	FSA NMG 202	ppm	20
Leachable fluoride content	FSA NMG 203	ppm	20
Ash content of graphite	DIN 51903	%	< 1
Cold compression value ϵ_{KSW}	DIN 28090-2	%	38
Cold rebound value ϵ_{KRW}	DIN 28090-2	%	4.3
Warm setting value $\epsilon_{WSW/300^\circ C}$	DIN 28090-2	%	1,2
Warm rebound value $\epsilon_{WRW/300^\circ C}$	DIN 28090-2	%	3.6
Operating conditions			
Minimum temperature		°C	-200
Continuous temperature			
Oxidizing atmosphere		°C	550
Reducing or inert atmosphere		°C	700
Pressure			
Demanding gasses		bar	60
Steam, gasses		bar	100
Liquids		bar	140




- Dimensions:** Plate sizes * 1000 mm x 1000 mm; 1500 mm x 1500 mm
 Thicknesses * 0.5 mm; 1.0 mm; 1.5 mm; 2.0 mm; 3.0 mm
 * Different sizes and thicknesses on request



Gaskets

Graphite sealings

Recommendations for use



- General suitability - Under common installation practices and chemical compatibility.
- Limited suitability – Technical consultation is mandatory.

Chemical resistance chart

Legend

<input checked="" type="checkbox"/>	Resistant
<input checked="" type="checkbox"/>	Resistance/ recommendation depends on operation conditions
<input checked="" type="checkbox"/>	Not resistant

Substance	<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	Substance	<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	Substance	<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>
Acetamide	<input checked="" type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	Dioxane	<input checked="" type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	Oleic acid	<input checked="" type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>
Acetic acid, 10 %	<input checked="" type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	Diphyl (Dowtherm A)	<input checked="" type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	Oleum (Sulfuric acid, fuming)	<input type="checkbox"/>	<input type="checkbox"/>	<input checked="" type="checkbox"/>
Acetic acid, 100 % (Glacial)	<input type="checkbox"/>	<input checked="" type="checkbox"/>	<input type="checkbox"/>	Esters	<input checked="" type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	Oxalic acid	<input type="checkbox"/>	<input checked="" type="checkbox"/>	<input type="checkbox"/>
Acetone	<input checked="" type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	Ethane (gas)	<input checked="" type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	Oxygen (gas)	<input checked="" type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>
Acetonitrile	<input checked="" type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	Ethers	<input checked="" type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	Palmitic acid	<input checked="" type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>
Acetylene (gas)	<input checked="" type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	Ethyl acetate	<input checked="" type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	Paraffin oil	<input checked="" type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>
Acid chlorides	<input type="checkbox"/>	<input checked="" type="checkbox"/>	<input type="checkbox"/>	Ethyl alcohol (Ethanol)	<input checked="" type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	Pentane	<input checked="" type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>
Acrylic acid	<input checked="" type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	Ethyl cellulose	<input checked="" type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	Perchloroethylene	<input checked="" type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>
Acrylonitrile	<input checked="" type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	Ethyl chloride (gas)	<input checked="" type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	Petroleum (Crude oil)	<input checked="" type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>
Adipic acid	<input checked="" type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	Ethylene (gas)	<input checked="" type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	Phenol (Carboic acid)	<input checked="" type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>
Air (gas)	<input checked="" type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	Ethylene glycol	<input checked="" type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	Phosphoric acid, 40 %	<input type="checkbox"/>	<input checked="" type="checkbox"/>	<input type="checkbox"/>
Alcohols	<input checked="" type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	Formaldehyde (Formalin)	<input checked="" type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	Phosphoric acid, 85 %	<input type="checkbox"/>	<input checked="" type="checkbox"/>	<input type="checkbox"/>
Aldehydes	<input checked="" type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	Formamide	<input checked="" type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	Phthalic acid	<input checked="" type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>
Alum	<input type="checkbox"/>	<input checked="" type="checkbox"/>	<input type="checkbox"/>	Formic acid, 10 %	<input type="checkbox"/>	<input checked="" type="checkbox"/>	<input type="checkbox"/>	Potassium acetate	<input checked="" type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>
Aluminium acetat	<input checked="" type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	Formic acid, 85 %	<input type="checkbox"/>	<input checked="" type="checkbox"/>	<input type="checkbox"/>	Potassium bicarbonate	<input checked="" type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>
Aluminium chlorate	<input checked="" type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	Formic acid, 100 %	<input type="checkbox"/>	<input checked="" type="checkbox"/>	<input type="checkbox"/>	Potassium carbonate	<input checked="" type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>
Aluminium chloride	<input type="checkbox"/>	<input type="checkbox"/>	<input checked="" type="checkbox"/>	Freon-12 (R-12)	<input checked="" type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	Potassium chloride	<input checked="" type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>
Aluminium sulfate	<input checked="" type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	Freon-134a (R-134a)	<input checked="" type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	Potassium cyanide	<input checked="" type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>
Amines	<input checked="" type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	Freon-22 (R-22)	<input checked="" type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	Potassium dichromate	<input type="checkbox"/>	<input checked="" type="checkbox"/>	<input type="checkbox"/>
Ammonia (gas)	<input checked="" type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	Fruit juices	<input checked="" type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	Potassium hydroxide	<input checked="" type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>
Ammonium bicarbonate	<input checked="" type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	Fuel oil	<input checked="" type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	Potassium iodide	<input checked="" type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>
Ammonium chloride	<input type="checkbox"/>	<input checked="" type="checkbox"/>	<input type="checkbox"/>	Gasoline	<input checked="" type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	Potassium nitrate	<input checked="" type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>
Ammonium hydroxide	<input checked="" type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	Gelatin	<input checked="" type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	Potassium permanganate	<input type="checkbox"/>	<input checked="" type="checkbox"/>	<input type="checkbox"/>
Amyl acetate	<input checked="" type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	Glycerine (Glycerol)	<input checked="" type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	Propane (gas)	<input checked="" type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>
Anhydrides	<input checked="" type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	Glycols	<input checked="" type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	Propylene (gas)	<input checked="" type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>
Aniline	<input checked="" type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	Helium (gas)	<input checked="" type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	Pyridine	<input checked="" type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>
Anisole	<input checked="" type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	Heptane	<input checked="" type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	Salicylic acid	<input checked="" type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>
Argon (gas)	<input checked="" type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	Hydraulic oil (Glycol based)	<input checked="" type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	Seawater/ brine	<input type="checkbox"/>	<input checked="" type="checkbox"/>	<input type="checkbox"/>
Asphalt	<input checked="" type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	Hydraulic oil (Mineral type)	<input checked="" type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	Silicones (oil/ greases)	<input type="checkbox"/>	<input checked="" type="checkbox"/>	<input type="checkbox"/>
Barium chloride	<input type="checkbox"/>	<input checked="" type="checkbox"/>	<input type="checkbox"/>	Hydraulic oil (Phosphate ester based)	<input checked="" type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	Soaps	<input checked="" type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>
Benzaldehyde	<input checked="" type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	Hydrazine	<input checked="" type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	Sodium aluminate	<input checked="" type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>
Benzene	<input checked="" type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	Hydrocarbons	<input checked="" type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	Sodium bicarbonate	<input checked="" type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>
Benzoic acid	<input checked="" type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	Hydrochloric acid, 10 %	<input type="checkbox"/>	<input type="checkbox"/>	<input checked="" type="checkbox"/>	Sodium bisulfite	<input checked="" type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>
Bio-diesel	<input checked="" type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	Hydrochloric acid, 37 %	<input type="checkbox"/>	<input type="checkbox"/>	<input checked="" type="checkbox"/>	Sodium carbonate	<input checked="" type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>
Bio-ethanol	<input checked="" type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	Hydrofluoric acid, 10 %	<input type="checkbox"/>	<input type="checkbox"/>	<input checked="" type="checkbox"/>	Sodium chloride	<input checked="" type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>
Black liquor	<input type="checkbox"/>	<input checked="" type="checkbox"/>	<input type="checkbox"/>	Hydrofluoric acid, 48 %	<input type="checkbox"/>	<input type="checkbox"/>	<input checked="" type="checkbox"/>	Sodium cyanide	<input checked="" type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>
Borax	<input checked="" type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	Hydrogen (gas)	<input checked="" type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	Sodium hydroxide	<input checked="" type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>
Boric acid	<input checked="" type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	Iron sulfate	<input checked="" type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	Sodium hypochlorite (Bleach)	<input type="checkbox"/>	<input type="checkbox"/>	<input checked="" type="checkbox"/>
Butadiene (gas)	<input checked="" type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	Isobutane (gas)	<input checked="" type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	Sodium silicate (Water glass)	<input checked="" type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>
Butane (gas)	<input checked="" type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	Isocetane	<input checked="" type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	Sodium sulfate	<input checked="" type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>
Butyl alcohol (Butanol)	<input checked="" type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	Isoprene	<input checked="" type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	Sodium sulfide	<input type="checkbox"/>	<input checked="" type="checkbox"/>	<input type="checkbox"/>
Butyric acid	<input checked="" type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	Isopropyl alcohol (Isopropanol)	<input checked="" type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	Starch	<input checked="" type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>
Calcium chloride	<input type="checkbox"/>	<input checked="" type="checkbox"/>	<input type="checkbox"/>	Kerosene	<input checked="" type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	Steam	<input checked="" type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>
Calcium hydroxide	<input checked="" type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	Ketones	<input checked="" type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	Stearic acid	<input checked="" type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>
Carbon dioxide (gas)	<input checked="" type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	Lactid acid	<input type="checkbox"/>	<input checked="" type="checkbox"/>	<input type="checkbox"/>	Styrene	<input checked="" type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>
Carbon monoxide (gas)	<input checked="" type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	Lead acetate	<input checked="" type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	Sugars	<input checked="" type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>
Cellosolve	<input checked="" type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	Lead arsenate	<input checked="" type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	Sulfur	<input checked="" type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>
Chlorine (gas)	<input type="checkbox"/>	<input checked="" type="checkbox"/>	<input type="checkbox"/>	Magnesium sulfate	<input checked="" type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	Sulfur dioxide (gas)	<input checked="" type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>
Chlorine (in water)	<input type="checkbox"/>	<input type="checkbox"/>	<input checked="" type="checkbox"/>	Maleic acid	<input checked="" type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	Sulfuric acid, 20 %	<input type="checkbox"/>	<input type="checkbox"/>	<input checked="" type="checkbox"/>
Chlorobenzene	<input checked="" type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	Malic acid	<input type="checkbox"/>	<input checked="" type="checkbox"/>	<input type="checkbox"/>	Sulfuric acid, 98 %	<input type="checkbox"/>	<input type="checkbox"/>	<input checked="" type="checkbox"/>
Chloroform	<input checked="" type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	Methane (gas)	<input checked="" type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	Sulfuryl chloride	<input type="checkbox"/>	<input type="checkbox"/>	<input checked="" type="checkbox"/>
Chloroprene	<input checked="" type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	Methyl alcohol (Methanol)	<input checked="" type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	Tar	<input checked="" type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>
Chlorosilanes	<input checked="" type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	Methyl chloride (gas)	<input checked="" type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	Tartaric acid	<input type="checkbox"/>	<input checked="" type="checkbox"/>	<input type="checkbox"/>
Chromic acid	<input checked="" type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	Methylene dichloride	<input checked="" type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	Tetrahydrofuran (THF)	<input checked="" type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>
Citric acid	<input checked="" type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	Methyl ethyl ketone (MEK)	<input checked="" type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	Titanium tetrachloride	<input type="checkbox"/>	<input type="checkbox"/>	<input checked="" type="checkbox"/>
Copper acetate	<input checked="" type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	N-Methyl-pyrrolidone (NMP)	<input checked="" type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	Toluene	<input checked="" type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>
Copper sulfate	<input checked="" type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	Milk	<input checked="" type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	2,4-Toluenediisocyanate	<input checked="" type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>
Creosote	<input checked="" type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	Mineral oil (ASTM no. 1)	<input checked="" type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	Transformer oil (Mineral type)	<input checked="" type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>
Cresols (Cresylic acid)	<input checked="" type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	Motor oil	<input checked="" type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	Trichloroethylene	<input checked="" type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>
Cyclohexane	<input checked="" type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	Naphtha	<input checked="" type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	Vinegar	<input checked="" type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>
Cyclohexanol	<input checked="" type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	Nitric acid, 10 %	<input type="checkbox"/>	<input type="checkbox"/>	<input checked="" type="checkbox"/>	Vinyl chloride (gas)	<input checked="" type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>
Cyclohexanone	<input checked="" type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	Nitric acid, 65 %	<input type="checkbox"/>	<input type="checkbox"/>	<input checked="" type="checkbox"/>	Vinylidene chloride	<input checked="" type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>
Decalin	<input checked="" type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	Nitrobenzene	<input checked="" type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	Water	<input checked="" type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>
Dextrin	<input checked="" type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	Nitrogen (gas)	<input checked="" type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	White spirits	<input checked="" type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>
Dibenzyl ether	<input checked="" type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	Nitrous gases (NO _x)	<input type="checkbox"/>	<input checked="" type="checkbox"/>	<input type="checkbox"/>	Xylenes	<input checked="" type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>
Dibutyl phthalate	<input checked="" type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	Octane	<input checked="" type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	Xylenol	<input checked="" type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>
Dimethylacetamide (DMA)	<input checked="" type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	Oils (Essential)	<input checked="" type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	Zinc sulfate	<input checked="" type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>
Dimethylformamide (DMF)	<input checked="" type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	Oils (Vegetable)	<input checked="" type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>		<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>

The recommendations made here serve only as a guideline for the selection of a suitable gasket. Since the function and durability of a gasket depends on a large number of factors, the information provided cannot be used to substantiate warranty claims. If there are special approval regulations, these must be observed.